

Data Sheet

PLASTRONFOAM ROTA

Application: foaming agent for the rotomoulding of polyethylene

Active Ingredients: endothermic multi-component system, based on sodium bicarbonate and citric acid derivatives

Active Content: 100%

Physiology: the raw materials used, correspond to the recommendations of the European Directives

Supplied as: white, free-flowing powder

Technical Data:

Decomp. Start.: > 130°C

Processing Temp.: for a optimum gas yield, a processing temperature between 180°C and 210°C is recommended

Dosage:

Rotomoulding: 1.5% - 2%

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually.

All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.