

Data Sheet

PLASTSTATIC 50 PE

Application: Internal and external antistatic agent for polyolefin; it gives almost instantaneous antistatic performance. However in some cases the effect might be only temporarily.

Active Ingredients: Fatty acid esters

Active Content: 50 %

Carrier: modified polyethylene

Physiology: EEC No limitations for all polymers
USA No limitations for all polymers

Supplied as: whitish granules

Technical data:

Applicable for: PE, PP

Dosage:

<i>Polyolefin films:</i>	< 50 µm	0.3 – 0.5 %
	> 50 µm	0.5 – 1.0 %

<i>moulded articles:</i>	depending on the wall thickness:	0.5 - 1.0 %
---------------------------------	----------------------------------	-------------

Storage: It is recommended to store the PLASSTATIC 50 PE preferably below 30°C

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually. All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.