

## Data Sheet

## PLASTSTATIC 50 PE

**Application:** Internal and external antistatic agent for polyolefin; it gives almost instantaneous antistatic performance. However in some cases the effect might be only temporarily.

***Active Ingredients:*** Fatty acid esters

***Active Content:*** 50 %

***Carrier:*** modified polyethylene

***Physiology:*** EEC No limitations for all polymers

USA No limitations for all polymers

***Supplied as:*** whitish granules

**Technical data:**

***Applicable for:*** PE, PP

**Dosage:**

<b><i>Polyolefin films:</i></b>	< 50 µm	0.3 – 0.5 %
	> 50 µm	0.5 – 1.0 %

<b><i>moulded articles:</i></b>	depending on the wall thickness:	0.5 - 1.0 %
---------------------------------	----------------------------------	-------------

**Storage:** It is recommended to store the PLASSTATIC 50 PE preferably below 30°C

The information given in this data sheet is based on many years of practical experience. Nevertheless can it only be a recommendation and a basis for practical testing, where the optimum dosage has to be determined individually.  
All information given herein is only a recommendation. Its use shall remain the sole responsibility of the customer. No patent guarantee whatsoever shall be implied.